

# Vanberg Specialized Coatings

## Armorcoat UV Data Sheet



---

---

### PROFESSIONAL COATINGS

---

---

#### PRODUCT DESCRIPTION:

**ARMORCOAT UV** comes from a new generation of epoxy formulations that exhibits 'Ultimate' color and gloss retention (even in exterior applications). **ARMORCOAT UV** is a two-component 100% solids epoxy coating designed for applications where superior UV protection over color quartz, flake, stain (and other decorative floors) is needed.

#### RECOMMENDED USAGE:

**ARMORCOAT UV** is VOC compliant and meets all USDA guidelines for use in federally inspected facilities. **ARMORCOAT UV** provides long-lasting UV protection and non-yellowing characteristics as a topcoat for most VSC floor or Wall coating systems, including stained floors, decorative floor and wall overlays, warehouses, shop floors, agricultural facilities, kitchens, restrooms and other areas where a high build and UV resistant coating is needed.

#### FEATURES:

- Excellent UV resistance
- Cleans Easily
- Clear is Water-Clear
- Gloss Finish
- Good Chemical Resistance
- Good Abrasion Resistance
- Single or Multiple Coat Application
- No Induction Time

#### PACKAGING INFORMATION:

- 1.5 gallon (5.6L) unit #AC205 (Clear)
- 3 gallon (11.35L) unit packaged in two proportioned 1.5 gallon (5.6) units
- **CLEAR TEXTURE COAT:** 1.5 gal (5.6L) unit

GENERAL PRODUCT DATA	
Mix Ratio (volume)	2 parts Resin to 1 part Hardener
Recommended Thickness	10 – 16 (mils)
Application Temperature	55°- 85° F with relative humidity below 75% for best results.
Solids Content (%)	100% (+/- 1%)
Viscosity (mixed)	450 – 600 CPS Typical
Hardness (Shore D)	70 – 75 (ASTM D-2240)
Gloss (60°F)	90 – 100
VOC	0 g/l (EPA method 24)
UV Resistance	Excellent (QUV)
Shelf Life	1 year (unopened, stored at 55°-85° F)

CURE SCHEDULE	
Pot Life	20 - 30 minutes @ 75° F
Tack Free (dry to touch)	8-10 hours @ 75° F
Recoat or Topcoat	14 - 16 hours @ 75° F.
Light Foot Traffic	18 hours @ 75° F
Heavy Traffic	24 – 48 hours @ 75° F

#### COVERAGE:

This product should be applied at the rate of approximately 100 - 160 sq. ft. per gallon (3.68m<sup>2</sup>/ L), which is approximately 16 - 10 mils. As with all coatings, coverage is dependent on the smoothness and porosity of the surface. Since this product is 100% solids, it can be applied as thick as needed. For **ARMOR-ROCK** and **ARMOR-SLATE** systems add 25-30 lbs. of selected VSC aggregate to each 1.5 gal. mix. See VSC SYSTEM APPLICATION GUIDES for details.

#### SURFACE PREPARATION:

The substrate must be clean, dry and sound with new concrete cured for at least 30 days at 70°F (21°C). A moisture test is recommended. Remove dust, laitance, grease, curing compounds, waxes, foreign particles, disintegrated or soft base materials, and any previously applied potentially incompatible coatings. Create a surface profile on the surface by steel shot blasting, mechanical abrasion or acid etching. Repair cracks and joints with **VSC's EPOXY GEL, JOINT-FILL** or other repair products. For additional concrete preparation information and methods, refer to VSC's Surface Preparation Guide. If the concrete surface is not prepared properly, product adhesion can be a problem.

#### FOR BEST RESULTS:

- Use for interior use.
- New concrete must cure for at least 30 days @ 70F (21°C).
- DO NOT thin EPOXY.
- DO NOT use when humidity exceeds 75% indoors.
- DO NOT allow material to puddle during application.
- Allow each coat to dry tack-free before recoating.
- Apply each coat within 24 hours of previous coat.
- Discard any material subjected to freezing.
- DO NOT apply to structurally unsound surfaces.
- Prime bare concrete with a suitable VSC primer.
- Apply a test patch to ensure adhesion.

#### PRIMING:

For optimum results, prime the prepared concrete floor first with a recommended VSC primer.

Allow the VSC primer to dry thoroughly before mixing and applying the next coating. The primed floor should be tack free.

**Review VSC'S Material Safety Data Sheets (MSDS and Data Sheet) for the primer prior to mixing and applying.**

#### MIXING:

Avoid mixing and application of this product if the floor temperature is below 55F (10°C) or above 85F (29°C). Also avoid application if the humidity is higher than 75% R.H. indoors. The product temperature should be at or near 70°F. The temperature of the floor, materials and air in the area of the installation all play a role in how the product will apply and cure. **For pre-packaged kits:** Carefully pour entire contents of Hardener and the Resin into a 5-gallon container. DO NOT change the ratio of Hardener to Resin. Blend thoroughly for 2 to 3 minutes with a spiral-mixing blade (PROP MIXER available from VSC) attached to a low-speed (400-600 RPM) 1/2 inch electric drill. Take care not to induce air into the

material during mixing. This will cause "bubbles" in the coating when applied.

For information on application situations not covered above, contact your VSC representative.

**For bulk units:** Portion out Hardener and Resin into a clean 5 gallon (18.9 L) pail according to the mix ratio on the front of this data sheet. Mix thoroughly as stated above.

**POT LIFE:**

At 75F (23.9°C) and 50% R.H., this epoxy has a useful pot life of approximately 20-30 minutes. Using any product beyond the useful life will result in variable results and therefore any mixed product beyond the pot life should be discarded. Apply all material to the floor as quickly as possible to increase working time. If product begins to heat or steam do not put it on the floor (Discard).

**APPLICATION:**

The recommended application of this product involves pouring it in a narrow line directly onto the concrete surface and then spreading it with a serrated or flat bladed squeegee. Use a brush or 4" epoxy roller along edges and around equipment (cut-in). Spread the coating in a continuous manner from one side of the area being coated to the other. Spread the epoxy at the decided upon coverage rate. Immediately follow with a 3/8" (.95 cm) nap epoxy roller cover. The epoxy should be rolled as evenly as possible to eliminate spike shoe and squeegee marks. Overlap the next column to be rolled by at least 1/2" (1.3cm) with the previously rolled column. Avoid excess rolling of the epoxy with the roller to avoid splatter and lessen chances of bubbling of the final film. To achieve a smooth surface, or to best cover imperfections in the floor, it is recommended to roll the coating with a spiked or looped roller. The individual(s) applying the epoxy should be wearing "spiked sandals" available from VSC. Allow the epoxy to cure thoroughly before mixing and applying the next coat (if used). It should be tack-free before recoating. If the humidity gets very high, the product may exhibit a "blush". This can be removed with a solvent wipe or by screening before applying the next coat.

**CLEAN UP:**

Use **SOLVENT 101** or xylol.

**DISPOSAL:**

Empty containers may contain product residue, including flammable or combustible vapors. Do not cut, puncture or weld near these containers. Label warnings must be observed until containers have been commercially cleaned or reconditioned. Containers to be thrown out must be disposed of in accordance with federal, state and local regulations. Use only licensed hazardous waste disposal companies if required.

**MAINTENANCE:**

For optimal floor appearance and performance following installation, refer to VSC's Floor Maintenance Instructions.

**CUSTOMER NOTE:**

---

**WARRANTY STATEMENT**

Information about VSC products is given to the best of our knowledge, based on tests and experience. Such information supplied about our products is not a representation or a warranty. It is supplied on the condition that you will make your own tests to determine the suitability of the product for your particular purpose. As products are often applied or used under conditions beyond our control, VSC cannot guarantee anything but the quality of its products. VSC warrants that its products meet the specifications set forth by VSC, but we reserve the right to change any given specification without prior notice. VSC DISCLAIMS ALL WARRANTIES RELATING TO THE PRODUCTS AND THEIR APPLICATION, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Receipt of VSC products constitutes acceptance of the terms of this limited warranty and the terms and the conditions set out in our invoice, contrary provisions of buyer's purchase documents not withstanding. Upon receipt of merchandise, purchaser has 30 days to notify VSC in writing that materials are defective. In the event VSC finds that the product delivered is off specification, VSC will, at its sole discretion, either replace the product or refund the purchase price thereof, and VSC's choice of one of these remedies is the buyer's sole remedy. In no event shall the liability of VSC exceed the purchase price of shipped merchandise. Claims must be in writing. Claims after 30 days are void. VSC will under no circumstances be liable for special, incidental or consequential damages. This warranty supercedes all other guarantees, whether oral or written, and whether expressed, implied or statutory. No representative is authorized to make any representation or warranty or assume any other liability on our behalf with any sale of our products. Certain products may contain chemicals which may cause serious physical injury. Before using, please read the Material Safety Data Sheet and follow all precautions to prevent bodily harm.



**VANBERG SPECIALIZED COATINGS**  
**PO BOX 19414**  
**LENEXA, KS 66285-9414**

**August 8, 2012**  
**Data Sheets/Armorcoat UV (CRK)**